

Performance Definition

Actual performance in concrete per A.S.T.M. C-1399 ARS:

ARS P.S.I. Range	0 ↔ 50 psi	50 ↔ 125 psi	125 ↔ 300 psi
Function	Plastic Shrinkage	Shrinkage/Temperature – WWF	Structural
Description	Monofilament	Fibrillated Polypropylene	Macrosynthetic
Dosage	1/2 lb. – 1.5 lbs.	1.5 lbs. – 3.0 lbs.	3.0 lbs. – 7.5 lbs.