



MACRO SYNTHETIC

Description

FORTA® FERRO-GREEN® is a unique blend of macro synthetic fibers designed specifically for pervious concrete applications. The FERRO-GREEN blend consists of 100% recycled polypropylene fibrillated fibers and high-performance twisted-bundle monofilament fibers that are designed to mix, distribute, and finish well. This fiber combination offers a variety of desirable benefits to pervious concrete pavement applications including increased strength, toughness, freeze-thaw and raveling resistance, and durability - all while preserving both the plastic and hardened concrete void structure.

Reinforcement Objective

To inhibit plastic and hardened shrinkage cracking of pervious concrete, and to increase its toughness, freeze-thaw resistance, and durability.

Physical Properties

Specific Gravity	0.91
Tensile Strength	83-96 ksi (570-660 MPa)
Length	2.25 in (54 mm), 1.5 in (38 mm), 0.75 in (19 mm)
Melting Point	319°F (160°C)
Material	Virgin Copolymer / Recycled Polypropylene
Form	Monofilament / Fibrillated
Color	Gray/Dark Gray
Acid / Alkali Resistance	Excellent
Absorption	Nil

Compliance & Certification

- ASTM C1116 / C1116M-10a, Standard Specification for Fiber-Reinforced Concrete, "Type III Synthetic Fiber-Reinforced Concrete"
- ASTM D7508 / D7508M-10(2015), Standard Specification for Polyolefin Chopped Strands for Use in Concrete
- DUNS: 094214129
- CAGE Code: 0AFN8
- NAICS: 325220

Applications

FERRO-GREEN is used to toughen any pervious concrete application such as driveways, curbs, sidewalks, and commercial parking lots and pavements. The use of this three-dimensionally distributed non-corrosive macro synthetic fiber blend is one of the few methods available to add true toughness reinforcement to pervious cross-sections, without reducing porosity. Contact FORTA for design assistance and dosage recommendations.

Performance Benefits

- Enhance durability
- Improve flexural toughness and fatigue resistance
- Increase impact and shear resistance
- Increase freeze-thaw and raveling resistance

Reinforcement Ratio

This product is typically used at a ratio of 0.17% to 0.5% by volume of pervious concrete depending on application and desired performance. Contact FORTA for design assistance and dosage recommendations.

Dosage by Volume (%)	Dosage by Weight	
	Imperial (lb/cu yd)	Metric (kg/cu m)
0.17	2.5	1.5
0.33	5.0	3.0
0.50	7.5	4.5

Packaging

FERRO-GREEN is available in convenient degradable mixer-ready bags in 1.0 to 5.0 lb increments (1.0 and 2.0 kg).

Recommendations

Addition: FERRO-GREEN is packaged in mixer-ready bags that can be added directly into the concrete mixing system. The fiber should be added during or after batching of the other ingredients – never as the first mix ingredient.

Mixing: When possible, add fibers to a rotating drum. Once all fibers have been added to the batch, mix four to five minutes at standard mixing speed. Road-revolution speed should not be counted as part of the required fiber mixing time.

Additional Information

Additional information such as the Safety Data Sheet, Certifications, videos and other literature can be found on the forta-ferro.com website. The website also features Project Profiles that show the many applications and benefits of FERRO-GREEN first-hand.



Pervious

Limited Warranty

FORTA® Products are warranted to be free of defects in material and will meet all published physical properties as set forth herein. EXCEPT FOR THE EXPRESS LIMITED WARRANTY SET FORTH HEREIN, NEITHER FORTA NOR ANY PERSON ON FORTA'S BEHALF HAS MADE OR MAKES ANY EXPRESS OR IMPLIED REPRESENTATION OR WARRANTY WHATSOEVER, EITHER ORAL OR WRITTEN, INCLUDING ANY WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, TITLE, OR NON-INFRINGEMENT, WHETHER ARISING BY LAW, COURSE OF DEALING, COURSE OF PERFORMANCE, USAGE OF TRADE OR OTHERWISE, ALL OF WHICH ARE EXPRESSLY DISCLAIMED.

The exclusive remedy for defective product is outlined in FORTA's Standard Terms and Conditions of Sale, available upon request. CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.

FORTA reserves the right to change the features and specifications of its products without prior notice.

FERRO-GREEN® can be purchased from FORTA or an authorized FORTA® products distributor, dealer or representative.

U.S. Patent Nos. 6,753,081 and 7,168,232. Additional patents pending.

FORTA®, FERRO-GREEN®, and "Circles of Strength" mark are registered trademarks of FORTA

© 2019 FORTA

FD.1.10.05.19