



MICRO SYNTHETIC

Description

FORTA® NYLO-MONO® is an easy to finish micro synthetic fiber, made of 100% virgin nylon monofilament. This fiber is designed to function as a plastic shrinkage reinforcement intended to reduce the formation of shrinkage cracks prior to initial set and to reduce settlement shrinkage. NYLO-MONO is non-corrosive, chemically inert, and resistant to acid and alkali attack.

Reinforcement Objective

To inhibit concrete cracking caused by plastic and settlement shrinkage that occurs prior to the initial set.

Physical Properties

Specific Gravity	1.14
Tensile Strength	140 ksi (966 MPa)
Length	0.25 in (6 mm), 0.5 in (12 mm), 0.75 in (19 mm)
Melting Point	509°F (265°C)
Material	Virgin Nylon
Form	Monofilament
Color	White
Acid / Alkali Resistance	Good
Absorption	Nil

Compliance & Certification

- ASTM C1116 / C1116M-10a, Standard Specification for Fiber-Reinforced Concrete, "Type III Synthetic Fiber-Reinforced Concrete"
- ASTM D7508 / D7508M-10 (2015), Standard Specification for Polyolefin Chopped Strands for Use in Concrete
- Evaluated by ICC-ES, see Evaluation Report No. ESR-2720
- UL Listed: CBXQ.R18552 and CBXQ7.R18552
- DUNS: 094214129
- CAGE Code: 0AFN8
- NAICS: 325220



Applications

NYLO-MONO is primarily used with cast-in-place concrete applications such as slabs-on-ground, overlays/toppings, curbs, driveways, sidewalks, basement floors, garage floors, and colored concrete – anywhere that the objective is to control plastic shrinkage cracking. Requires no mix design or placement changes!

Performance Benefits

- Increase surface durability
- Reduce plastic and settlement shrinkage
- Reduce settlement and bleeding
- Provide 3-dimensional reinforcement against micro-cracking

Recommended Dosage

This product is typically used at a minimum dosage rate of 1.0 lb/cu yd (0.6 kg/cu m) of concrete. Contact FORTA for design assistance and dosage recommendations.

Packaging

	Domestic	International
Bags	1.0 lb	0.6 kg
Cartons	50 bags	40 bags
Pallets	16 cartons/800 bags	12 cartons/480 bags

Recommendations

Addition: NYLO-MONO is packaged in mixer-ready bags that can be added directly into the concrete mixing system. The fiber should be added during or after batching of the other ingredients – never as the first mix ingredient.

Mixing: When possible, add fibers to a rotating drum. Once all fibers have been added to the batch, mix four to five minutes at standard mixing speed. Road-revolution speed should not be counted as part of the required fiber mixing time.

Slump: Fibers may reduce the visual slump measured by the slump-cone test, but has a lesser effect on flow-ability and workability. To regain any loss of workability or slump, the use of appropriate admixtures is recommended – avoid the addition of water.

Additional Information

Additional information such as the Safety Data Sheet, Certifications, videos and other literature can be found on the forta-ferro.com website. The website also features Project Profiles that show the many applications and benefits of FORTA products first-hand.

Limited Warranty

FORTA® Products are warranted to be free of defects in material and will meet all published physical properties as set forth herein. EXCEPT FOR THE EXPRESS LIMITED WARRANTY SET FORTH HEREIN, NEITHER FORTA NOR ANY PERSON ON FORTA'S BEHALF HAS MADE OR MAKES ANY EXPRESS OR IMPLIED REPRESENTATION OR WARRANTY WHATSOEVER, EITHER ORAL OR WRITTEN, INCLUDING ANY WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, TITLE, OR NON-INFRINGEMENT, WHETHER ARISING BY LAW, COURSE OF DEALING, COURSE OF PERFORMANCE, USAGE OF TRADE OR OTHERWISE, ALL OF WHICH ARE EXPRESSLY DISCLAIMED.

The exclusive remedy for defective product is outlined in FORTA's Standard Terms and Conditions of Sale, available upon request. CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.

FORTA reserves the right to change the features and specifications of its products without prior notice.

NYLO-MONO® can be purchased from FORTA or an authorized FORTA® products distributor, dealer or representative.

FORTA®, NYLO-MONO®, and "Circles of Strength" mark are registered trademarks of FORTA

© 2019 FORTA

FD.1.05.05.19